



FIBERS & TEXTILES COMPANY

High-Performance Materials For Your Hardworking Products

### 1260/2 Nylon 66 Tirecord (RT)

Properties	Min	Max	Units
Single Cord Adhesion	3.00	15.00	LBf
Dip Pickup	4.20	6.00	%
Elongation at Specified Load	6.80	10.00	%@15LB
SQYDW	9.40	10.20	OZ/YD <sup>2</sup>
Tensile	45.19	N/A	LBS
Shrinkage	5.80	8.80	%
Ultimate Elongation	10.00		%
Width	49.50	50.50	IN
Ends/Inch	28.00	± .5	EPI
Warp Yarn	1260 denier N66 2ply		
Cable Twist	9.50	10.30	TPI
Ply Twist	9.50	10.30	TPI
Gauge	0.025	0.028	IN
Fill Yarn	20/1 Tencel		
Shell	7" OD 1 3/8 Square Openings		